

CHAPTER 2: BONDING AND PROPERTIES

ISSUES TO ADDRESS...

- What promotes bonding?
- What types of bonds are there?
- What properties are inferred from bonding?



Atomic Structure (Freshman Chem.)

- atom – electrons – 9.11×10^{-31} kg
 protons } 1.67×10^{-27} kg
 neutrons
- atomic number = # of protons in nucleus of atom
 = # of electrons of neutral species
- A [=] atomic mass unit = amu = 1/12 mass of ^{12}C

Atomic wt = wt of 6.023×10^{23} molecules or atoms

$$1 \text{ amu/atom} = 1\text{g/mol}$$

C 12.011
H 1.008 etc.



Atomic Structure

- Valence electrons determine all of the following properties
 - 1) Chemical
 - 2) Electrical
 - 3) Thermal
 - 4) Optical



Electronic Structure

- Electrons have wavelike and particulate properties.
 - This means that electrons are in **orbitals** defined by a probability.
 - Each orbital at discrete energy level determined by **quantum numbers**.

Quantum

n = principal (energy level-shell)

ℓ = subsidiary (orbitals)

m_l = magnetic

m_s = spin

Designation

K, L, M, N, O (1, 2, 3, etc.)

s, p, d, f (0, 1, 2, 3, ..., $n-1$)

1, 3, 5, 7 ($-\ell$ to $+\ell$)


$\frac{1}{2}, -\frac{1}{2}$



Electron Energy States

Electrons...

- have discrete **energy states**
- tend to occupy lowest available energy state.



SURVEY OF ELEMENTS

- Most elements: Electron configuration **not stable**.

<u>Element</u>	<u>Atomic #</u>	<u>Electron configuration</u>
Hydrogen	1	$1s^1$
Helium	2	$1s^2$ (stable)
Lithium	3	$1s^2 2s^1$
Beryllium	4	$1s^2 2s^2$
Boron	5	$1s^2 2s^2 2p^1$
Carbon	6	$1s^2 2s^2 2p^2$
...
Neon	10	$1s^2 2s^2 2p^6$ (stable)
Sodium	11	$1s^2 2s^2 2p^6 3s^1$
Magnesium	12	$1s^2 2s^2 2p^6 3s^2$
Aluminum	13	$1s^2 2s^2 2p^6 3s^2 3p^1$
...
Argon	18	$1s^2 2s^2 2p^6 3s^2 3p^6$ (stable)
...
Krypton	36	$1s^2 2s^2 2p^6 3s^2 3p^6 3d^{10} 4s^2 4p^6$ (stable)

Adapted from Table 2.2,
Callister 7e.


- Why? **Valence** (outer) shell usually not filled completely.



Electron Configurations


- Valence electrons – those in unfilled shells
- Filled shells more stable
- Valence electrons are most available for bonding and tend to control the chemical properties

– example: C (atomic number = 6)



Electronic Configurations

ex: Fe - atomic # = 26 $1s^2 2s^2 2p^6 3s^2 3p^6$ $3d^6 4s^2$



Adapted from Fig. 2.4,
Callister 7e.



The Periodic Table

- Columns: Similar Valence Structure

IA	IIA	IIIB	IVB	VB	VIB	VIIB	VIII			IB	IIB	IIIA	IVA	VA	VIA	VIIA	0
1 H	2 He						26 Fe	27 Co	28 Ni	29 Cu	30 Zn	5 B	6 C	7 N	8 O	9 F	10 Ne
3 Li	4 Be						23 V	24 Cr	25 Mn			13 Al	14 Si	15 P	16 S	17 Cl	18 Ar
11 Na	12 Mg	21 Sc	22 Ti	23 V	24 Cr	25 Mn	26 Fe	27 Co	28 Ni	29 Cu	30 Zn	31 Ga	32 Ge	33 As	34 Se	35 Br	36 Kr
19 K	20 Ca	39 Y	40 Zr	41 Nb	42 Mo	43 Tc	44 Ru	45 Rh	46 Pd	47 Ag	48 Cd	49 In	50 Sn	51 Sb	52 Te	53 I	54 Xe
37 Rb	38 Sr	Rare earth series	72 Hf	73 Ta	74 W	75 Re	76 Os	77 Ir	78 Pt	79 Au	80 Hg	81 Tl	82 Pb	83 Bi	84 Po	85 At	86 Rn
55 Cs	56 Ba	Acti-nide series	104 Rf	105 Db	106 Sg	107 Bh	108 Hs	109 Mt	110 Ds								
87 Fr	88 Ra																

Adapted from Fig. 2.6, Callister 7e.

Electropositive elements:
Readily give up electrons
to become + ions.

Electronegative elements:
Readily acquire electrons
to become - ions.



Electronegativity

- Ranges from 0.7 to 4.0,
- Large values: tendency to acquire electrons.

IA																		0
H																		He
2.1	IIA											IIIA	IVA	VA	VIA	VIIA		-
Li	Be											B	C	N	O	F		Ne
1.0	1.5											2.0	2.5	3.0	3.5	4.0		-
Na	Mg																	Ar
0.9	1.2											Al	Si	P	S	Cl		-
		IIIB	IVB	VB	VIB	VIIIB	VIII			IB	IIB							
K	Ca	Sc	Ti	V	Cr	Mn	Fe	Co	Ni	Cu	Zn	Ga	Ge	As	Se	Br		Kr
0.8	1.0	1.3	1.5	1.6	1.6	1.5	1.8	1.8	1.8	1.9	1.6	1.6	1.8	2.0	2.4	2.8		-
Rb	Sr	Y	Zr	Nb	Mo	Tc	Ru	Rh	Pd	Ag	Cd	In	Sn	Sb	Te	I		Xe
0.8	1.0	1.2	1.4	1.6	1.8	1.9	2.2	2.2	2.2	1.9	1.7	1.7	1.8	1.9	2.1	2.5		-
Cs	Ba	La-Lu	Hf	Ta	W	Re	Os	Ir	Pt	Au	Hg	Tl	Pb	Bi	Po	At		Rn
0.7	0.9	1.1-1.2	1.3	1.5	1.7	1.9	2.2	2.2	2.2	2.4	1.9	1.8	1.8	1.9	2.0	2.2		-
Fr	Ra	Ac-No																
0.7	0.9	1.1-1.7																



Smaller electronegativity



Larger electronegativity

Adapted from Fig. 2.7, *Callister 7e*. (Fig. 2.7 is adapted from Linus Pauling, *The Nature of the Chemical Bond*, 3rd edition, Copyright 1939 and 1940, 3rd edition. Copyright 1960 by Cornell University.)







Ionic bond – metal + nonmetal

↑
donates
electrons

↑
accepts
electrons


Dissimilar electronegativities

ex: MgO



Ionic Bonding


- Occurs between + and - ions.
- Requires **electron transfer**.
- Large difference in electronegativity required.
- Example: NaCl



Ionic Bonding

- Energy – minimum energy most stable
 - Energy balance of attractive and repulsive terms

$$E_N = E_A + E_R = -\frac{A}{r} - \frac{B}{r^n}$$



Adapted from Fig. 2.8(b),
Callister 7e.



Examples: Ionic Bonding

- Predominant bonding in **Ceramics**

IA																	0	
H																	He	
2.1	IIA											IIIA	IVA	VA	0	VIA	VIIA	
Li	Be											B	C	N	O	F	Ne	
1.0	1.5											2.0	2.5	3.0	3.5	4.0	-	
Na	Mg											Al	Si	P	S	Cl	Ar	
0.9	1.2	IIIB	IVB	VB	VIB	VIIIB	VIII				IB	IIB	1.5	1.8	2.1	2.5	3.0	-
K	Ca	Sc	Ti	V	Cr	Mn	Fe	Co	Ni	Cu	Zn	Ga	Ge	As	Se	Br	Kr	
0.8	1.0	1.3	1.5	1.6	1.6	1.5	1.8	1.8	1.8	1.9	1.6	1.6	1.8	2.0	2.4	2.8	-	
Rb	Sr	Y	Zr	Nb	Mo	Tc	Ru	Rh	Pd	Ag	Cd	In	Sn	Sb	Te	I	Xe	
0.8	1.0	1.2	1.4	1.6	1.8	1.9	2.2	2.2	2.2	1.9	1.7	1.7	1.8	1.9	2.1	2.5	-	
Cs	Ba	La-Lu	Hf	Ta	W	Re	Os	Ir	Pt	Au	Hg	Tl	Pb	Bi	Po	At	Rn	
0.7	0.9	1.1-1.2	1.3	1.5	1.7	1.9	2.2	2.2	2.2	2.4	1.9	1.8	1.8	1.9	2.0	2.2	-	
Fr	Ra	Ac-No																
0.7	0.9	1.1-1.7																



Give up electrons



Acquire electrons

Adapted from Fig. 2.7, *Callister 7e*. (Fig. 2.7 is adapted from Linus Pauling, *The Nature of the Chemical Bond*, 3rd edition, Copyright 1939 and 1940, 3rd edition. Copyright 1960 by Cornell University.)




Covalent Bonding

- similar **electronegativity** \therefore share electrons
- bonds determined by valence – *s* & *p* orbitals dominate bonding
- Example: CH₄

C: has 4 valence e⁻,
needs 4 more

H: has 1 valence e⁻,
needs 1 more

Electronegativities
are comparable.



Adapted from Fig. 2.10, *Callister 7e*.



Primary Bonding

- **Metallic Bond** -- delocalized as electron cloud
- **Ionic-Covalent Mixed Bonding**

$$\% \text{ ionic character} = \left(1 - e^{-\frac{(X_A - X_B)^2}{4}} \right) \times (100\%)$$

where X_A & X_B are Pauling electronegativities

Ex: MgO

$$\begin{aligned} X_{\text{Mg}} &= 1.3 \\ X_{\text{O}} &= 3.5 \end{aligned}$$


$$\% \text{ ionic character} = \left(1 - e^{-\frac{(3.5 - 1.3)^2}{4}} \right) \times (100\%) = 70.2\% \text{ ionic}$$




SECONDARY BONDING

Arises from interaction between dipoles

- Fluctuating dipoles



- Permanent dipoles-molecule induced




Summary: Bonding

Type	Bond Energy	Comments
Ionic	Large!	Nondirectional (ceramics)
Covalent	Variable large-Diamond small-Bismuth	Directional (semiconductors , ceramics polymer chains)
Metallic	Variable large-Tungsten small-Mercury	Nondirectional (metals)
Secondary	smallest	Directional inter-chain (polymer) inter-molecular




Properties From Bonding: T_m


- Bond length, r



- Bond energy, E_0



- Melting Temperature, T_m




T_m is larger if E_0 is larger.



Properties From Bonding : α


- Coefficient of thermal expansion, α



coeff. thermal expansion

$$\frac{\Delta L}{L_0} = \alpha (T_2 - T_1)$$

- $\alpha \sim$ symmetry at r_0



α is larger if E_0 is smaller.



Summary: Primary Bonds

Ceramics

(Ionic & covalent bonding):

Large bond energy

large T_m

large E

small α

Metals

(Metallic bonding):

Variable bond energy


moderate T_m

moderate E

moderate α

Polymers

(Covalent & Secondary):



Directional Properties

Secondary bonding dominates

small T_m

small E

large α



ANNOUNCEMENTS

Reading:

Core Problems:

Self-help Problems:

